

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Serial No: 09/775,760

Group Art Unit: 1623

Inventor(s): Mallon et al.

Filed: 2/2/01

Title: PRODUCTION OF POLYSACCHARIDE ETHERS

PRELIMINARY AMENDMENT

Hon. Assistant Commissioner for Patents  
Washington, DC 20231

Sir:

Prior to the initial examination of the above-identified  
patent application, please amend the application as follows:

In the Claims

Please amend claims 1-32 without prejudice.

Please add new claims 33-51 as follows:

33. In a process for producing polysaccharide ethers  
comprising:

(i) treating polysaccharide with a basic compound to  
promote swelling of the polysaccharide;

(ii) reacting the polysaccharide with at least one  
derivatizing agent in a liquid medium comprising at least one  
organic solvent under conditions effective to promote a reaction  
between the polysaccharide and the derivatizing agent and form  
a reaction product comprising a polysaccharide ether, the basic  
compound and the organic solvent and a residue of the  
polysaccharide;

(iii) treating at least a portion of the reaction product  
comprising the basic compound with an acidic compound to  
provide a neutralized liquid comprising a salt of the acidic  
compound and the basic compound; and

Date of Deposit: MAY 21 2001 EXPRESS MAIL  
Mailing Label No. FL1803890774S  
I hereby certify that this paper or file is being  
deposited with the United States Postal Service  
Express Mail Post Office to Addressee service  
under 37 CFR 1.10 on the date indicated above  
and is addressed to the Commissioner of Patents  
and Trademarks, Washington, D.C. 20231

FL1803890774S  
Carolyn Vandergriфт  
(Typed or stamped name of person  
mailing paper or file)  
Carolyn Vandergriфт  
(Signature of person mailing paper  
or file)

(iv) separating the polysaccharide ether from at least one of the reaction product or the neutralized liquid:

The improvement which comprises:

(a) subjecting the neutralized liquid to a first separation at an alkaline pH to separate the salt from the organic solvent and the residue of the polysaccharide and provide a purified, neutralized liquid; and

(b) subjecting the purified, neutralized liquid to an electric current and suitable means effective to promote the conversion the salt to the acidic compound and the basic compound.

34. The process of claim 33 which provides an acid product stream comprising the acidic compound.

35. The process of claim 33 which provides a base product stream comprising the basic compound.

36. The process of claim 33 further comprising utilizing at least a portion of the acid product stream in step (iii) of claim 1.

37. The process of claim 33 further comprising utilizing at least a portion of the base product stream in step (i) of claim 1.

38. The process of claim 33 wherein said subjecting of the purified, neutralized liquid with the electric current is conducted in the presence of a bipolar membrane effective to provide a source of hydrogen and hydroxyl ions.

39. The process of claim 33 wherein the first separation is conducted by electrodialysis with a semi-permeable membrane..

40. The process of claim 39 wherein the pH is effective to inhibit the deposition of the residue of the polysaccharide on the membrane.
41. The process of claim 40 wherein the pH is greater than about 10.
42. The process of claim 41 wherein the pH is from about 10.5 to 14.
43. The process of claim 33 wherein the electric current has a current density of from about 500 to 2000 amps per square meter.
44. The process of claim 33 wherein the organic solvent is selected from the group consisting of acetone, ethanol, isopropyl alcohol, t-butyl alcohol, mono-, di-, and triethylene glycol and mixtures thereof.
45. The process of claim 33 wherein the basis compound is selected from the group consisting of sodium hydroxide, potassium hydroxide, calcium hydroxide, magnesium hydroxide, lithium hydroxide, ammonium hydroxide and mixtures thereof.
46. The process of claim 33 wherein the acidic compound is selected from the group consisting of acetic acid, nitric acid, hydrochloric acid, sulfuric acid, phosphoric acid and mixtures thereof.
47. The process of claim 33 wherein the polysaccharide is selected from the group consisting of cellulose, starch, pectin, chitosan,

chitin, agar, carrageenan, alginate, guar, arabic, tragacanth, xanthan gum and mixtures thereof.

48. The process of claim 33 wherein the derivatizing agent is an alkylene oxide selected from the group consisting of ethylene oxide, propylene oxide, butylene oxide and mixtures thereof.

49. The process of claim 33 which further comprises derivatizing the polysaccharide ether with at least one cationic, anionic or hydrohobic substituent.

50. In a process for producing cellulose ethers comprising:

(i) treating cellulose with a basic compound to promote swelling of the cellulose;

(ii) reacting the cellulose with at least one derivatizing agent in a liquid medium comprising at least one organic solvent under conditions effective to promote a reaction between the cellulose and the derivatizing agent and form a reaction product comprising a cellulose ether, the basic compound and the organic solvent and a residue of the cellulose;

(iii) treating at least a portion of the reaction product comprising the basic compound with an acidic compound to provide a neutralized liquid comprising a salt of the acidic compound and the basic compound; and

(iv) separating the cellulose ether from at least one of the reaction product or the neutralized liquid:

The improvement which comprises:

(a) subjecting the neutralized liquid to a first separation by electrodialysis with a semi-permeable membrane at an alkaline pH to separate the salt from the organic solvent

and the residue of the cellulose and provide a purified, neutralized liquid; and

(b) subjecting the purified, neutralized liquid to an electric current and suitable means effective to promote the conversion the salt to the acidic compound and the basic compound.

51. The process of claim 50 wherein the pH is effective to inhibit the deposition of the residue of the cellulose on the membrane.

# REMARKS

The claims have been amended to define more clearly the invention. The following table provides a cross-reference between the claim numbers and the old claim numbers.

## CLAIMS CROSS-REFERENCE

<u>NEW CLAIM</u>	<u>OLD CLAIM (SUPPORT)</u>
33	22 and 1
34	2
35	3
36	4
37	5
38	23
39	24
40	26
41	27
42	28
43	9
44	11
45	17

<u>NEW CLAIM</u>	<u>OLD CLAIM (SUPPORT)</u>
46	18
47	19
48	20
49	21
50	22 and 24
51	26

The above table also indicates where basis can be found.

An early and favorable Office Action is courteously solicited.

Respectfully submitted,



Warren K. Volles  
Reg. No. 33,810  
Attorney for Applicant(s)  
37 C.F.R. 1.34(a)  
(203) 794-6360

Union Carbide Corporation  
Danbury, Connecticut 06817-0001  
Dated: May 21, 2001  
PAT 160A:5.98